


GEOGRID POLGRID BX 25/25



PROPERTIES	TEST METHOD	IMPERIAL			METRICS		
		UNIT	VALUE	TOLERANCE	UNIT	VALUE	TOLERANCE
MATERIAL							
Material	Polymer PP						
Unit Weight		oz/ft ²	0.82	±0.08	g/m ²	250	±25
Minimum carbon black		%	2		%	2	
MECHANICAL							
Peak tensile strength	EN ISO 10319	lb/ft	1919/1919	-206	kN/m	28/28	-3
Tensile strength at 2% strain MD/CMD	EN ISO 10319	lb/ft	617/617		kN/m	9/9	
Tensile strength at 5% strain MD/CMD	EN ISO 10319	lb/ft	1233/1233		kN/m	18/18	
Elongation at MAX load							
Along the band	EN ISO 10319	%	11	±1.5	%	11	±1.5
Band width			10	±1.5		10	±1.5
Junction efficiency	EN ISO 10319	%	100		%	100	
PHYSICAL							
Durability	Predicted to be durable for a minimum of 100 years in natural soils with 4< pH <9 and at soil temperatures <77°F (25°C) on the basis of durability assessment report BTTG 10/23388 and related test results To be covered within 1 month after installation						
Aperture size - MD		in	1.53	±0.16	mm	39	±4
Aperture size - CMD		in	1.53	±0.16	mm	39	±4
DELIVERY							
Roll length		ft	164	±1%	mm	50	±1%
Roll width		ft	13.1	±1%	mm	4	±1%

