


GEOGRID
POLGRID BX 30/30



PROPERTIES	TEST METHOD	IMPERIAL			METRICS		
		UNIT	VALUE	TOLERANCE	UNIT	VALUE	TOLERANCE
MATERIAL							
Material		Polymer PP					
Unit Weight		oz/ft ²	0.98	±0.1	g/m ²	300	±30
Minimum carbon black		%	2		%	2	
MECHANICAL							
Peak tensile strength	EN ISO 10319	lb/ft	2261/2261	-206	kN/m	33/33	-3
Tensile strength at 2% strain MD/CMD	EN ISO 10319	lb/ft	822/822		kN/m	12/12	
Tensile strength at 5% strain MD/CMD	EN ISO 10319	lb/ft	1576/1576		kN/m	23/23	
Elongation at MAX load							
Along the band	EN ISO 10319	%	11	±1.5	%	11	±1.5
Band width			10	±1.5		10	±1.5
Junction efficiency	EN ISO 10319	%	100		%	100	
PHYSICAL							
Durability	Predicted to be durable for a minimum of 100 years in natural soils with 4< pH <9 and at soil temperatures <77°F (25°C) on the basis of durability assessment report BTTG 10/23388 and related test results To be covered within 1 month after installation						
Aperture size - MD		in	1.53	±0.16	mm	39	±4
Aperture size - CMD		in	1.53	±0.16	mm	39	±4
DELIVERY							
Roll length		ft	164	±1%	mm	50	±1%
Roll width		ft	13.1	±1%	mm	4	±1%

